



MPX 2800 Balewrap

FEATURES

- Polystyrene-based raw materials with high concentrations of butadiene rubber
- Bi-axially oriented for maximum strength
- Easily heat-sealed during wrapping
- Designed to be directly consumed along with rubber bales during processing
- High haze - matte surface – high rubber content inclusion product
- Excellent toughness and puncture resistance
- Exceeds all requirements for CONEG, Proposition 65 & Natural Latex levels

TECHNICAL SPECIFICATIONS	Typical Value	Units	ASTM
Average Thickness	3 75	mils µm	ASTM D 6988
Web Range	20-70 50.8-177.8	in. cm.	MPX
Film Yield	8961.9 12.682	in. ² /lb. sq.m./kg	ASTM D 4321
Coefficient of Friction	0.50	-	ASTM D 1894
Dart Drop Impact	> 7.8	ft-lbs	ASTM D 4272
Transmission	> 80	%	ASTM D 1003
Haze	>85	%	ASTM D 1003
Clarity	< 8	%	ASTM D 1003
Gloss @ 60° angle	< 10	%	ASTM D 1003
% Butadiene, Titration	16.0-17.0	%	MPX
Tensile Strength @ Break MD TD	5,500 (37.92) 6,000 (41.39)	Psi (MPa) Psi (MPa)	ASTM D 882
% Elongation MD TD	100-160 80-130	% %	ASTM D 882
1% Secant Modulus MD TD	160 (1103.2) 180 (1241.1)	Kpsi (MPa) Kpsi (MPa)	ASTM D 882

The information herein is to the best of our knowledge, true, and accurate. However, since conditions of use are beyond our control, all recommendations or suggestions are presented without guarantee or responsibility on our part. No warranty is made or implied.

FOR MORE INFORMATION CONTACT OUR SALES DEPARTMENT AT 888.456.8018