



2700 OPS Lamination Film

CAPABILITIES

- Gauge: .001" to .004" (28 to 101 μm)
- Width: 2" to 80" (50.8 to 2032 mm)
- Core Size: 3" and 6" standard cores, 8" available
- Roll O.D.: various configurations available
- Custom Colors and tints available
- Matte and gloss available
- Corona treatment available

PROPERTIES

- Exceptional clarity and stiffness
- Superb yield
- Superior dimensional stability
- Great for laminating to EDS and HIPS
- Excellent ink adhesion
- Ideal for metallizing applications
- FDA compliant CFR 21 #177.1640
- Kosher material

TECHNICAL SPECIFICATIONS

| | Value | Units | ASTM |
|---------------------------|-------------------------|---------------------------------------|------|
| Specific Gravity | 1.05 | grams/cm ² | |
| Yield | 26,360 | in ² /lb./mil of thickness | |
| Tensile Strength at Yield | 8,000 to 12,000 | psi | D638 |
| Ultimate Elongation | 3 to 10 | % | D638 |
| Tensile Modulus | 400,000 to 450,000 | psi | D790 |
| Typical Range of Use | 0 to 175 (-17 to 79) | °F (°C) | |

CHEMICAL RESISTANCE

| | |
|----------------------|-------------------|
| Acid Resistance | Good to Excellent |
| Strong Oxidizers | Poor |
| Alkalies | Excellent |
| Hydrocarbon Solvents | Poor |
| Alcohols | Good to Excellent |
| Fat, Grease, and Oil | Good |

The information herein, is to the best of our knowledge, true, and accurate. However, since conditions of use are beyond our control, all recommendations or suggestions are presented without guarantee or responsibility on our part. No warranty is made or implied.

FOR MORE INFORMATION CONTACT OUR SALES DEPARTMENT AT 888.456.8018